

CUSTOMER REFERENCE

COMCORK SPORTS PROFILE 3.2 mm

Sample description as provided by customer
COMCORK SPORTS PROFILE 3.2 mm
Ref PO WPO-14689

TEST METHOD ISO 9239-1(2010 06-15) Determination of the Burning Behaviour using a radiant heat source As required by the New Zealand Building Code Clause C3.4 (b) (April 2012)

The test values relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be the sole criterion for assessing the potential fire hazard of the product. Clause 10 (o) of ISO 9239-1:2010.

Conditioning as specified in BS EN 13238.2001

Sample submitted Date June 2014

Test Date 07 Jul 2014

ASSEMBLY SYSTEM: DIRECT STICK MAPEI ADESILEX G 19

The floor covering was directly stuck to the substrate using MAPEI ADESILEX G 19 adhesive.

Substrate: Non-Combustible

Substrate - 6mm Fibre Reinforced Cement Board to simulate a Non-Combustible Flooring.

The Holding Torque on Specimen Frame was 2Nm.



Initial Test Specimen 1 Length Direction Critical Radiant Flux 8.2 kW/m²
Specimen 1 Width Direction Critical Radiant Flux 8.1 kW/m²
Full tests carried out in the Width Direction

SPECIMEN	Width #1	Width #2	Width #3	Mean
Critical Radiant Flux (kW/m ²)	8.1	7.4	8.2	7.9

The value quoted below is as required by the New Zealand Building Code Clause C3.4 (b) (April 2012) "Minimum critical radiant flux when tested to ISO 9239-1:2010". Hence the Radiant Flux quoted is the value at Flame-Out/Extinguishment Not after a 30 minute burn as used in Europe.

MEAN CRITICAL RADIANT FLUX 7.9 kW/m²

OBSERVATIONS: The samples shrunk away from the heat source, ignited and burnt a short distance.

 ACCREDITED FOR TECHNICAL COMPETENCE	M. B. Webb Technical Manager	
	DATE: 7/7/2014	
	Performance & Approvals Testing No. 15393	
	Accredited for compliance with ISO/IEC 17025.	

PAGE 1 of 2

Clause 10 (o) of ISO 9239-1:2010

The values on Page 2 have no relevance to the Code.

1004 04 09

TIME FOR EACH SPECIMEN TO REACH EACH MARKER IN SECONDS

Specimen	50	60	110	160	210	260	310	360	410	460	510	560	610	660	710	760	810	860
1	217	218	285	325	558	0	/											
2	243	244	333	378	505	564	/											
3	248	249	342	407	569													

TESTS

BURNING CHARACTERISTICS

Specimen	Burn Length (mm) at Flame Out/ Extinguishment	Time To Burn Out (s)
Initial Test: Length	242	844
Specimen Tests: Width		
1	250	800
2	280	913
3	244	921
Mean	258	878



ACCREDITED FOR
**TECHNICAL
COMPETENCE**



M. B. Webb
Technical Manager

DATE: 07 Jul 2014

Performance and Approvals
Testing No. 15393
Accredited for compliance
with ISO/IEC 17025.

The laboratory does not allow the use of this page of the report without the use of page 1.
This page alone has no validity under Clause 10 (o) of ISO 9239-1:2010
2004 04 09 3870 7 July 2014